

Casing - Production Range

Range Lengths:	Range 1	Range 2	Range 3	Extra long	max. length variation
(ft)	18.0 - 25.0	25.0 - 34.0 (95% 28ft min)	34.0 - 48.0 (95% 36ft min)	48.0 - 65.00	5
(m)	5,49 - 7,62	7,62 - 10,36 (95% 8,53m min)	10,36 - 14,63 (95% 10,97m min)	14,63 - 18,29	1,52

Labels

Nominal linear mass shown for information and assistance in ordering only (T&C: threaded and coupled)

Type of end finish available
P: Plain end, S: Short round thread, L: Long round thread, B: Buttress thread
HC: High Collapse, Q&T: Quench and Tempered

OD (inch)	T&C Nominal linear mass (lb/ft)	OD (mm)	T&C Nominal linear mass (kg/m)	External Upset T&C Nominal Linear mass (kg/m)	Wall Thickness (inch)	Wall Thickness (mm)	H40	J55 / K55	L80 and L80 HC Q&T	N80 Q&T	MB80 (proprietary as welded 80 grade)	P110 and P110 HC Q&T
4.5	9.50	114,30	14,14	14,14	0.205	5,21	PS	PS	-	-	-	-
4.5	10.50	114,30	15,63	15,63	0.224	5,89	-	PSB	-	-	-	-
4.5	11.60	114,30	17,26	17,26	0.250	6,35	-	PSLB	PLB	PLB	PLB	PLB
4.5	13.50	114,30	20,09	20,09	0.290	7,37	-	-	PLB	PLB	PLB	PLB
4.5	15.10	114,30	22,47	22,47	0.337	8,56	-	-	-	-	-	PLB
5	11.50	127,00	17,11	17,11	0.220	5,59	-	PS	-	-	-	-
5	13.00	127,00	19,35	19,35	0.253	6,43	-	PSLB	-	-	-	-
5	15.00	127,00	22,32	22,32	0.296	7,52	-	PSLB	PLB	PLB	PLB	PLB
5	18.00	127,00	26,79	26,79	0.362	9,19	-	-	PLB	PLB	PLB	PLB
5.5	14.00	139,70	20,83	20,83	0.244	6,20	PS	PS	-	-	-	-
5.5	15.50	139,70	23,07	23,07	0.275	6,98	-	PSLB	-	-	-	-
5.5	17.00	139,70	25,30	25,30	0.304	7,72	-	PSLB	PLB	PLB	PLB	PLB
5.5	20.00	139,70	29,76	29,76	0.361	9,17	-	-	PLB	PLB	PLB	PLB
6.625	20.00	168,28	29,76	29,76	0.288	7,32	PS	PSLB	-	-	-	-
6.625	24.00	168,28	35,72	35,72	0.352	8,94	-	PSLB	PLB	PLB	PLB	PLB
6.625	28.00	168,28	41,67	41,67	0.417	10,59	-	-	PLB	PLB	PLB	PLB
6.625	32.00	168,28	47,62	47,62	0.475	12,06	-	-	PLB	PLB	PLB	PLB
7	17.00	177,80	25,30	25,30	0.231	5,87	PS	-	-	-	-	-
7	20.00	177,80	29,76	29,76	0.272	6,91	PS	PS	-	-	-	-
7	23.00	177,80	34,23	34,23	0.317	8,05	-	PSLB	PLB	PLB	PLB	PLB
7	26.00	177,80	38,69	38,69	0.362	9,19	-	PSLB	PLB	PLB	PLB	PLB
7	29.00	177,80	43,16	43,16	0.408	10,36	-	-	PLB	PLB	PLB	PLB
7	32.00	177,80	47,62	47,62	0.453	11,51	-	-	PLB	PLB	PLB	PLB
7.625	24.00	193,68	35,72	35,72	0.300	7,62	PS	PS	-	-	-	-
7.625	26.40	194,68	39,29	39,29	0.328	8,33	-	PSLB	PLB	PLB	PLB	PLB
7.625	29.70	195,68	44,20	44,20	0.375	9,52	-	-	PLB	PLB	PLB	PLB
7.625	33.70	196,68	50,15	50,15	0.430	10,92	-	-	PLB	PLB	PLB	PLB
7.625	39.00	196,68	58,04	58,04	0.500	12,70	-	-	PLB	PLB	PLB	PLB
8.625	24.00	219,08	35,72	35,72	0.264	6,71	-	PS	-	-	-	-
8.625	28.00	219,08	41,67	41,67	0.304	7,72	PS	-	-	-	-	-
8.625	32.00	219,08	47,62	47,62	0.352	8,94	PS	PSLB	-	-	-	-
8.625	36.00	219,08	53,57	53,57	0.400	10,16	-	PSLB	PLB	PLB	PLB	PLB
8.625	40.00	219,08	59,53	59,53	0.450	11,43	-	-	PLB	PLB	PLB	PLB
8.625	44.00	219,08	65,48	65,48	0.500	12,70	-	-	PLB	PLB	PLB	PLB
9.625	32.30	244,48	48,07	48,07	0.312	7,92	PS	-	-	-	-	-
9.625	36.00	244,48	53,57	53,57	0.352	8,94	PS	PSLB	-	-	-	-
9.625	40.00	244,48	59,53	59,53	0.395	10,03	-	PSLB	PLB	PLB	PLB	-
9.625	43.50	244,48	64,73	64,73	0.435	11,05	-	-	PLB	PLB	PLB	PLB
9.625	47.00	244,48	69,94	69,94	0.472	11,99	-	-	PLB	PLB	PLB	PLB
10.75	32.75	273,05	48,74	48,74	0.279	7,09	PS	-	-	-	-	-
10.75	40.50	273,05	60,27	60,27	0.350	8,89	PS	PSB	-	-	-	-
10.75	45.50	273,05	67,71	67,71	0.400	10,16	-	PSB	-	-	-	-
10.75	51.00	273,05	75,90	75,90	0.450	11,43	-	PSB	PSB	PSB	PSB	PSB
10.75	55.50	273,05	82,59	82,59	0.495	12,57	-	-	PSB	PSB	PSB	PSB
11.75	42.00	298,45	62,50	62,50	0.333	8,46	PS	-	-	-	-	-
11.75	47.00	298,45	69,94	69,94	0.375	9,53	-	PSB	-	-	-	-
11.75	54.00	298,45	80,36	80,36	0.435	11,05	-	PSB	-	-	-	-
11.75	60.00	298,45	89,29	89,29	0.489	12,42	-	PSB	PSB	PSB	PSB	PSB
13.375	48.00	339,72	71,43	71,43	0.330	8,38	PS	-	-	-	-	-
13.375	54.50	339,72	81,10	81,10	0.380	9,65	-	PSB	-	-	-	-
13.375	61.00	339,72	90,78	90,78	0.430	10,92	-	PSB	-	-	-	-
13.375	68.00	339,72	101,19	101,19	0.480	12,19	-	PSB	PSB	PSB	PSB	PSB
13.375	72.00	339,72	107,15	107,15	0.514	13,06	-	-	PSB	PSB	PSB	PSB